

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **03169504 A**

(43) Date of publication of application: **23.07.91**

(51) Int. Cl.

B27K 3/50
B27K 3/15

(21) Application number: **01308888**

(22) Date of filing: **30.11.89**

(71) Applicant: **MIROKU KIHAN KK**

(72) Inventor: **ABE KENICHI**
SHIMOYABU MASAYO

**(54) MODIFIED WOODY MATERIAL AND MODIFYING
METHOD FOR WOODY MATERIAL**

(57) Abstract

PURPOSE: To achieve stabilization of the size of the title material while maintaining its workability by impregnating the material with a polyacrylic acid/polyvalent metal salt and a thermosetting synthetic resin.

CONSTITUTION: A modified woody material is impregnated with a polyacrylic acid/polyvalent metal

salt and a thermosetting synthetic resin. The acrylic acid/polyvalent metal salt may be the acrylate of at least one member of polyvalent metals selected especially from among aluminum, zinc, copper and magnesium. The water-soluble precursor of the thermosetting synthetic resin is a precursor such as, for example, a urea resin, a melamine resin and a phenol resin, which has water-solubility. It may also be a prepolymer or the like, and a dimethylethylenurea is preferably used.

COPYRIGHT: (C)1991,JPO&Japio

XP-002159134

AN - 1991-257832 [35]

A - [001] 014 028 03- 034 04- 040 06- 07- 074 077 08- 080 081 10- 134 135
137 139 140 147 157 175 18& 180 185 186 189 19- 191 198 20- 230 231
239 262 264 265 266 27& 273 293 31- 311 316 318 336 341 344 346 398
40- 431 438 44& 473 477 48- 541 542 544 57- 58& 58- 59& 679 681 688
689 691 720 723 726

AP - JP19890308888 19891130; JP19890308888 19891130; [Based on J03169504]

CPY - MIRO-N

DC - A82 F09 P63

DR - 1740-U

FS - CPI;GMPI

IC - B27K3/15 ; B27K3/50

KS - 0013 0059 0071 0134 0185 0218 0224 0229 0231 0502 0506 0586 0590 1212
1214 1233 1235 1276 1277 1279 1517 1588 1731 1737 1756 2014 2020 2021
2024 2025 2043 2064 2066 2122 2152 2271 2288 2289 2295 2299 2300 2318
2432 2509 2604 2606 3152 3205 3268 3318

MC - A04-F04 A10-E22 A12-B09 F05-B01

PA - (MIRO-N) MIROKU KIHAN KK

PN - JP3169504 A 19910723 DW199135 000pp

- JP5039761B B 19930616 DW199327 B27K3/15 005pp

PR - JP19890308888 19891130

XA - C1991-111998

XIC - B27K-003/15 ; B27K-003/50

XP - N1991-196470

AB - J03169504 Wood is modified by impregnating polyvalent metal polyacrylate salt and a thermosetting synthetic resin into the material.

- The metallic salt is pref. Al, Zn, Cu or Mg polyacrylate, used as aq. soln. in a concn. of 10 - 20 wt.%. Pref. used together with a water-soluble radically copolymerisable monomer (pref. polyethylene glycol methacrylate in concn. = 5-10 wt.%). The water-soluble precursor of thermosetting synthetic resin is e.g., a precursor of urea resin, melamine resin or phenol resin and pref. dimethylolethylene urea and used in a concn. of 5 - 10 wt.%. The aq. soln. is blended with a radical initiator (e.g. a peroxide or an azo cpd.) and a condensing catalyst for the thermosetting resin (e.g., an alkanolamine) and pref. a surfactant (e.g., a quaternary ammonium salt in a concn. = up to 1 wt.%).

- ADVANTAGE - The modified material has high dimensional stability during drying and wetting. Has high putrefaction resistance and high resistance against the attack by insects and high sawing, planing and nailing workability. (5pp Dwg.No.0/3)

IW - MODIFIED WOOD MATERIAL IMPREGNATE POLYVALENT METAL POLYACRYLATE SALT
THERMOSETTING SYNTHETIC RESIN WOOD HIGH DIMENSION STABILISED
IKW - MODIFIED WOOD MATERIAL IMPREGNATE POLYVALENT METAL POLYACRYLATE SALT
THERMOSETTING SYNTHETIC RESIN WOOD HIGH DIMENSION STABILISED

NC - 001

OPD - 1989-11-30

ORD - 1991-07-23

PAW - (MIRO-N) MIROKU KIHAN KK

TI - Modifying wood material - by impregnating polyvalent metal

**polyacrylate salt and thermosetting synthetic resin into wood, for
high dimensional stability**